

DATA SHEET

/ ECOKRAFT BAGS

PAPER QUALITY EB														
TECHNICAL CHARACTERISTICS														
UNE / EN / ISO - 536	GRAMMAGE	g/m ²	50	60	70	80	90	100	110	115	120	125	200	
UNE / EN / ISO- 287	Moisture	%	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	+/- 1,5
UNE / EN / ISO - 1924 / 2	Stretch MD	%	2,0	2,0	2,0	2,0	2,0	2,0	2,0	2,0	2,0	2,0	2,0	-10%
UNE / EN / ISO - 1924 / 2	Stretch CD	%	5,5	5,5	6,0	6,0	6,0	6,0	6,0	6,0	6,0	6,0	6,0	-10%
UNE / EN / ISO - 1924 / 2	Lenght strength MD	m	6.500	6.500	8.700	8.700	8.700	8.700	8.700	8.700	8.700	8.700	8.700	-10%
UNE / EN / ISO - 1924 / 2	Lenght strength CD	m	3.000	3.000	3.200	3.200	3.200	3.200	3.200	3.200	3.200	3.200	3.200	-10%
UNE / EN / ISO - 1924 / 2	Tensile Index MD	Nm/g	64	64	85	85	85	85	85	85	85	85	85	-10%
UNE / EN / ISO - 1924 / 2	Tensile Index CD	Nm/g	29	29	31	31	31	31	31	31	31	31	31	-10%
UNE / EN / ISO - 535	Cobb 60 T	g/m ²	30	30	30	30	30	30	30	30	30	30	30	MAX. 40
UNE / EN / ISO - 535	Cobb 60 B	g/m ²	30	30	30	30	30	30	30	30	30	30	30	MAX. 40
EN / ISO - 2758	Burst Index	kPa m ² /g	3,2	3,2	3,8	3,8	3,8	3,8	3,8	3,8	3,8	3,8	3,6	Indicative
UNE / ISO 5636-5	Gurley (air resistance)	S	35	40	50	55	60	65	70	70	75	80	90	Indicative



UNE / EN / ISO - 20187	SAMPLE CONDITIONING	
	Relative humidity	50 +/- 2 %
	Temperature	23 +/- 1°C

MD: Machine Direction
CD: Cross Direction
T: Top
B: Bottom

OBSERVATIOS: For the other grammages of the nominals ones indicated in the table, values of the grammages immediately below shall be applied
Grammage tolerance $\pm 4\%$ to 100 g/m², $\pm 3\%$ to 200 g/m²

SEDE CENTRAL
Avenida Diagonal 403 6to.3
08008 Barcelona
T. +34 933 042 860
alier@aliersa.com

FÁBRICA DE PAPEL
Km. 10 de la carretera N-230
de Lleida al Valle de Arán
25124 Rosselló (Lleida)
T. +34 973 732 705
alierlle@aliersa.com